## **TEST REPORT**

DATE: 03-	18-2016		TEST NUMBER:	0226748

CLIENT Egetaepper a/s

TEST METHOD CONDUCTED	ASTM	D5252	Standard	Practice	for	the	Operation	of	the
IEST METHOD CONDUCTED	Hexap	ood Tumb	le Drum Te	ster					



DESCRIPTION OF TEST SAMPLE			
IDENTIFICATION	Contra Stripe ECT350		
CONSTRUCTION	Loop Pile		
BACKING	Attached Cushion		

## **GENERAL PRINCIPLE**

The test specimen is subjected to "Hexapod" tumbling in 2,000 cycle increments. A "Windsor" Versamatic upright beater bar vacuum was used to make four forward and backward passes along the length of the specimen after each 2,000 cycles.

After the requested number of cycles has been completed, the test specimen is assessed by three technicians for appearance change in accordance with the CRI standard reference scale and color change using the AATCC Gray Scale.

## **TEST RESULTS**

NUMBER OF CYCLES	APPEARANCE RATING	COLOR CHANGE RATING
12,000	3.5	4.0

	APPEARANCE RATING KEY		COLOR CHANGE RATING KEY
5	Excellent: No visual change noticeable	5	Negligible or no change
4	Good: Slight change due to disturbance of pile	4	Slight change
3	Fair: Noticeable change due to pile disturbance or matting	3	Moderate change
2	Poor: Loss of texture due to pile disturbance and/or matting	2	Considerable change
1	Very Poor: Severe pile disturbance and/or matting	1	Severe change

APPROVED BY:

Day aslewy

APPROVED BY:

NVLAP

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glernwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@op	tilink.us
--	-----------